



H 50133

POLYMER Test PY V4 KK**Product**

Top side

Bottom side

Standard EN 13707, EN 13969 (Typ A)**Application****Packaging** 20 rolls of 10 m x 1m = 200 m² per pallet

Characteristics	Testing method	Unit	Result
	EN 1848-1	m	10,0
	EN 1848-1	m	1,00
	EN 1848-1	mm/10m	< 20
	EN 1849-1	kg/m ²	NPD
	EN 1849-1	mm	3,6 (±0,2)
	EN 1928	kPa	60
	EN 13501-5	Klasse	NPD
	EN 13501-1	Klasse	E
	EN 12317-1	N/50mm	NPD
	EN 12311-1	N/50mm	370/250 (±100/±100)
	EN 12311-1	%	2/2 (±1/±1)
	EN 12691	mm	NPD
	EN 12730	kg	NPD
	EN 12310-1	N	75/75 (±25/±25)
	EN 1107-1	%	≤ 0,3
	EN 1109	°C	-5
	EN 1110	°C	100
	EN 1928	kPa	60
	EN 1931	μ	NPD

NPD = No performance determined

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.