

**H 51033  
BARUPLAN KV E 45 K****Product****Top side****Bottom side****Standard** EN 13707, EN 13969 (Typ A+T)**Application****Packaging** 18 rolls of 10 m x 1m = 180 m<sup>2</sup> per pallet

Characteristics	Testing method	Unit	Result
	EN 1848-1	m	10,0
	EN 1848-1	m	1,00
	EN 1848-1	mm/10m	< 20
	EN 1849-1	kg/m <sup>2</sup>	4,6 (±0,3)
	EN 1928	kPa	400
	EN 13501-5	Klasse	NPD
	EN 13501-1	Klasse	E
	EN 12317-1	N/50mm	≥ 500
	EN 12311-1	N/50mm	1000/800 (±200/±100)
	EN 12311-1	%	50/50 (±10/±10)
	EN 12691	mm	NPD
	EN 12730	kg	NPD
	EN 12310-1	N	220/220 (±50/±50)
	EN 1107-1	%	≤  0,6
	EN 1109	°C	-20
	EN 1110	°C	100
	EN 1928	kPa	400
	EN 1931	μ	NPD

NPD = No performance determined

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

**Subject to alteration without notice.**

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

**Development, Production and Sales of our products according to ISO 9001.**